

**Aluminium Alloy 1050 H14**
**Material Data Sheet**
**Scope**

Aluminium alloy 1050 is a popular grade of aluminium for general sheet metal work where moderate strength is required. Alloy 1050 is known for its excellent corrosion resistance, high ductility and highly reflective finish.

**Application**

This material is used for chemical process plant equipment, pyrotechnic powder, lamp reflectors, food industry containers, cable sheathing and architectural flashings.

**Supplied Forms**

- Shate
- Plain sheet
- Plain sheet with a PVC coating on one side
- Stucco sheet
- Stucco sheet with a PVC coating on one side

**Alloy Designations**

Aluminium alloy 1050 also corresponds to: AA1050A, S1B and A91050.

**Temper Types**

The most common tempers for 1050 aluminium are: H14 - Work hardened by rolling to half hard, not annealed after rolling.

**Fabrication**

- Solderability: Excellent
- Weldability - Gas: Excellent
- Weldability - Arc: Excellent
- Weldability - Resistance: Excellent
- Brazability: Excellent
- Workability - Cold: Excellent
- Machinability: Poor

**Welding**

When welding 1050 to itself or an alloy from the same sub-group the recommended filler wire is 1100. For welding to alloys 5083 and 5086 or alloys from the 7XXX series, the recommended wire is 5356. For other alloys use 4043 filler wire.

**Chemical Composition**

Element	% Present
Manganese (Mn)	0.0 - 0.05
Iron (Fe)	0.0 - 0.40
Copper (Cu)	0.0 - 0.05
Magnesium (Mg)	0.0 - 0.05
Silicon (Si)	0.0 - 0.25
Zinc (Zn)	0.0 - 0.07
Titanium (Ti)	0.0 - 0.05
Aluminium (Al)	Balance

**Mechanical properties at room temperature**

Property	Value
Proof Strength	85 MPa
Tensile Strength	100 MPa
Elongation	12 %
Shear Strength	60 MPa
Hardness Vickers	30 HV


Properties above are for material in the H14 condition

**Reference data for some physical properties (for guidance only)**

Property	Value
Density	2.71 Kg/m <sup>3</sup>
Melting Point	650 °C
Thermal Expansion	24 x 10 <sup>-6</sup> /K
Modulus of Elasticity	71 GPa
Thermal Conductivity	222 W/m.K
Electrical Resistivity	0.0282 x 10 <sup>-6</sup> Ω .m

**Editor**

ThyssenKrupp Materials (UK) Ltd  
 Cox's Lane  
 Cradley Heath  
 West Midlands  
 B64 5QU


**Important Note**

Information given in this data sheet about the condition or usability of materials respectively products are no warranty for their properties, but act as a description.

The information, we give on for advice, comply to the experiences of the manufacturer as well as our own. We cannot give warranty for the results of processing and application of the products.