

**Austenitic Corrosion Resistant Steel**

**Material Data Sheet**

Steel Designation:

Name

Material No.

**X2CrNiMo18-14-3**

**1.4435**

**Scope**

This data sheet applies to hot and cold rolled sheet and strip, semi-finished products, rods, rolled wire and profiles as well as seamless and welded tubes for pressure purposes.

**Application**

Construction encasement, doors, windows and armatures; offshore modules; cisterns and pipes for chemical tanks; production, warehousing and over land transportation of chemicals, food and beverages; pharmacy, synthetic fiber, paper and textile plants; pressure vessels.

Due to the low C-content, the resistance to **intergranular corrosion** is also guaranteed in the welded condition.

**Chemical composition (heat analysis in %)**

Product form	C	Si	Mn	P	S	N	Cr	Mo	Ni
C, H, P	≤ 0.030	≤ 1.00	≤ 2.00	≤ 0.045	≤ 0.015 <sup>1)</sup>	≤ 0.11	17.00 - 19.00	2.50 - 3.00	12.50 - 15.00
L	≤ 0.030	≤ 1.00	≤ 2.00	≤ 0.045	≤ 0.030 <sup>1)</sup>	≤ 0.11	17.00 - 19.00	2.50 - 3.00	12.50 - 15.00
T <sub>W</sub>	≤ 0.030	≤ 1.00	≤ 2.00	≤ 0.045 <sup>2)</sup>	≤ 0.015 <sup>2)</sup>	≤ 0.11	17.00 - 19.00	2.50 - 3.00	12.50 - 15.00
T <sub>S</sub>	≤ 0.030	≤ 1.00	≤ 2.00	≤ 0.040	≤ 0.015 <sup>1)</sup>	≤ 0.11	17.00 - 19.00	2.50 - 3.00	12.50 - 15.00

C = cold rolled strip; H = hot rolled strip; P = hot rolled sheet; L = semi-finished products, rods, rolled wire and profiles;

T<sub>W</sub> = welded tubes; T<sub>S</sub> = seamless tubes

<sup>1)</sup> For machinability, a controlled sulphur content of 0.015 - 0.030 % is recommended and permitted.

<sup>2)</sup> For tubes, which are welded without filler metal, P + S max. 0.040 %.

**Mechanical properties at room temperature in solution annealed condition**

Product form	Thickness mm <sub>max</sub>	Yield strength		Tensile strength R <sub>m</sub> N/mm <sup>2</sup>	Elongation		Impact energy (ISO-V) KV	
		R <sub>p0,2</sub> N/mm <sup>2</sup> <sub>min</sub>	R <sub>p1,0</sub> N/mm <sup>2</sup> <sub>min</sub>		A <sup>1)</sup> % <sub>min</sub> (longitudinal)	A <sup>1)</sup> % <sub>min</sub> (transverse)	J <sub>min</sub> (longitudinal)	J <sub>min</sub> (transverse)
C	8	240 <sup>3)</sup>	270 <sup>3)</sup>	550 - 700 <sup>3)</sup>	-	40	-	-
H	13,5	220 <sup>3)</sup>	260 <sup>3)</sup>	550 - 700 <sup>3)</sup>	-	40	100	60
P	75	220 <sup>3)</sup>	260 <sup>3)</sup>	520 - 670 <sup>3)</sup>	-	45	100	60
L	160	200 <sup>4)</sup>	235 <sup>4)</sup>	500 - 700 <sup>4)</sup>	40	-	100	-
L	250 <sup>2)</sup>	200 <sup>5)</sup>	235 <sup>5)</sup>	500 - 700 <sup>5)</sup>	-	30	-	60
T <sub>WS</sub>	60	190 <sup>6)</sup>	225 <sup>6)</sup>	490 - 690 <sup>6)</sup>	40	30	100	60

<sup>1)</sup> Gauge length and thickness according to DIN EN

<sup>2)</sup> > 160 mm

<sup>3)</sup> Transverse test piece, with product widths < 300 mm longitudinal test piece

<sup>7)</sup> min. 60 J at -196 °C

<sup>4)</sup> Longitudinal test piece

<sup>5)</sup> Transverse test piece

<sup>6)</sup> Longitudinal, external diameter > 508 mm transverse test piece

**Reference data on some physical properties (for guidance only)**

Density at 20 °C kg/dm <sup>3</sup>	Modulus of elasticity kN/mm <sup>2</sup> at				Thermal conductivity at 20 °C W/m K	Specific thermal capacity at 20 °C J/kg K	Specific electrical resistivity at 20 °C Ω mm <sup>2</sup> /m
	20 °C	200 °C	400 °C	500 °C			
8,0	200	186	172	165	15	500	0,75
Mean coefficient of thermal expansion 10 <sup>-6</sup> K <sup>-1</sup> between 20 °C and							
100 °C	200 °C		300 °C		400 °C		500 °C
16,0	16,5		17,0		17,5		18,0

**Guidelines on the temperatures for hot forming and heat treatment<sup>1)</sup>**

Hot forming		Heat treatment AT (solution annealed), Microstructure		
Temperature °C	Type of cooling	Temperature °C <sup>2) 3) 4)</sup>	Type of cooling	Microstructure
1150 to 850	Air	1030 to 1110	Water, air	Austenite with a low content of ferrite

- <sup>1)</sup> For simulative heat treated test pieces the temperatures for solution annealing have to be agreed.
- <sup>2)</sup> Solution annealing is in applicable, if the conditions for the hot forming and the concluding cooling are in such a way that the requirements for the mechanical properties of the product can be maintained.
- <sup>3)</sup> If heat treatment is carried out in a continuous annealing furnace, usually the upper area of the mentioned temperature range is preferred or even exceeded.
- <sup>4)</sup> For heat treatment within subsequent processing, the lower area of the stated temperature range for solution annealing has to be aspired, as otherwise the mechanical properties could be affected. If the lower limit for the solution annealing temperature was not undercut during hot forming, while repeating annealing a temperature of 1000 °C as the lower limit is sufficient.

**Processing / Welding**

Standard welding processes for these steel grades are:

- TIG-welding
- MAG-welding solid wire
- Arc welding (E)
- Submerged arc welding (SAW)
- Laser beam welding

Process	Filler metal		higher alloyed	
	Wire	Powder	Wire	Powder
TIG	similar			
	Thermanit GE-316 L	1.4430	Thermanit A	1.4576
MAG solid wire	similar		Thermanit 18/17 E	1.4440
	Thermanit GE-316 L Si	1.4430	Thermanit A Si	1.4576
Arc welding (E)	similar		Thermanit 18/17 E	1.4440
	Thermanit GE Spezial	1.4430	Thermanit AW	1.4576
	Thermanit GEW 316 L-17	1.4430	Thermanit 18/17 EW	1.4440
SAW	Thermanit GE-316L	Marathon 431 Marathon 213	Thermanit A Thermanit 18/17 E	Marathon 431+213 Marathon 104
	see page 3			

When choosing the filler metal, the corrosion stress has to be regarded, as well. The use of a higher alloyed filler metal can be necessary due to the cast structure of the weld metal.

A preheating is not necessary for this steel. A heat treatment after welding is normally not usual.

Austenitic steels only have 30 % of the thermal conductivity of non-alloyed steels. Their fusion point is lower than that of non-alloyed steels, therefore austenitic steels have to be welded with lower heat input than non-alloyed steels.

To avoid overheating or burn-thru of thinner sheets, higher welding speed has to be applied. Copper back-up plates for faster heat rejection are functional, whereas, to avoid cracks in the solder metal, it is not allowed to surface-fuse the copper back-up plate.

This steel has an extensively higher coefficient of thermal expansion as non-alloyed steel. In connection with a worse thermal conductivity, a greater distortion has to be expected.

When welding 1.4435 all procedures, which work against this distortion (e. g. back-step sequence welding, welding alternately on opposite sides with double-V butt weld, assignment of two welders when the components are accordingly large) have to be respected notably. For product thicknesses over 12 mm the double-V butt weld has to be preferred instead of a single-V butt weld. The included angle should be 60° - 70°, when using MIG-welding about 50° are enough. An accumulation of weld seams should be avoided. Tack welds have to be affixed with relatively shorter distances from each other (significantly shorter than these of non-alloyed steels), in order to prevent strong deformation, shrinking or flaking tack welds. The tacks should be subsequently grinded or at least be free from crater cracks.

1.4435 in connection with austenitic weld metal and too high heat input the addiction to form heat cracks exists. The addiction to heat cracks can be confined, if the weld metal features a lower content of ferrite (delta ferrite). Contents of ferrite up to 10 % have a favorable effect and do not affect the corrosion resistance generally. The thinnest layer as possible have to be welded (stringer bead technique) because a higher cooling speed decreases the addiction to hot cracks.

A preferably fast cooling has to be aspired while welding as well, to avoid the vulnerability to intergranular corrosion and embrittlement.

1.4435 is very suitable for **laser beam welding** (weldability A in accordance with DVS bulletin 3203, part 3). With a welding groove width smaller 0,3 mm respectively 0,1 mm product thickness the use of filler metals is not necessary. With larger welding grooves a similar filler metal can be used. With avoiding oxidation within the seam surface during laser beam welding by applicable backhand welding, e. g. helium as inert gas, the welding seam is as corrosion resistant as the base metal. A hot crack hazard for the welding seam does not exist, when choosing an applicable process.

1.4435 is also suitable for **laser beam fusion cutting** with nitrogen. The cut edges only have small heat affected zones and are generally free of micro cracks and thus are well formable. While choosing an applicable process the fusion cut edges can be converted directly. Especially, they can be welded without any further preparation.

While processing only stainless tools like steel brushes, pneumatic picks and so on are allowed, in order to not endanger the passivation.

It should be neglected to mark within the welding seam zone with oleigerous bolts or temperature indicating crayons.

The high corrosion resistance of this stainless steel is based on the formation of a homogeneous, compact passive layer on the surface. Annealing colors, scales, slag residues, tramp iron, spatters and such like have to be removed, in order to not destroy the passive layer.

For cleaning the surface the processes brushing, grinding, pickling or blasting (iron-free silica sand or glass spheres) can be applied. For brushing only stainless steel brushes can be used. Pickling of the previously brushed seam area is carried out by dipping and spraying, however, often pickling pastes or solutions are used. After pickling a carefully flushing with water has to be done.

### Remark

In quenched condition the material can be slightly magnetizable. With increasing cold forming the magnetizability increases.

### Editor

THYSSENKRUPP MATERIALS INTERNATIONAL GMBH  
Technical Sales / Quality Management  
Am Thyssenhaus 1  
45128 Essen

### References

DIN EN 10088-2:2005-09 Beuth Verlag GmbH, Postfach, D10772 Berlin  
DIN EN 10088-3:2005-09  
DIN EN 10216-5:2004-11  
DIN EN 10217-7:2005-05  
MB 821 "Properties" Informationsstelle Edelstahl Rostfrei, Postfach 10 22 05,  
MB 822 "The converting of stainless steel" D-4013 Düsseldorf  
DVS bulletin 3203, part 3 Verlag für Schweißen und Verwandte Verfahren DVS Verlag GmbH,  
Postfach 10 19 65, D-4010 Düsseldorf  
Laser beam electric arc cutting of stainless steels Thyssen Lasertechnik GmbH, Aachen  
Laser beam – longitudinal welding of profiles of stainless steel  
Böhler Schweisstechnik Deutschland GmbH, Hamm

### Important note

Information given in this data sheet about the condition or usability of materials respectively products are no warranty for their properties, but act as a description.  
The information, we give on for advice, comply for the experiences of the manufacturer as well as our own. We cannot give warranty for the results of processing and application of the products.

